

### Technical Specifications

Physical Property	U/M	Test Method	Value	Notes
Air Permeability		QI-104	3.0	Min.
Density	PCF	ASTM D-3574 -95	1.15	Test A
Elongation	%	ASTM D3574-96	130	Min. Test D
Flammability		MVSS-302	Meets	
Indentation Force Deflection	PSI	ASTM D-3574-95	32	Test B1 +/-3
Tear Strength	PIW	ASTM D-3574-96	1.0	Min. Test F
Tensile Strength	PSI	ASTM D-3575-96	12	Min.