

Specifications

Cork Rubber combines the compressibility and recovery characteristics of cork with the flexibility of rubber, making it an excellent product for a wide range of applications.

Physical Properties

Physical Property	Test Method	Unit	Value
Density	ASTM D3676	PCF	37.5
Tensile Strength	ASTM F152	PSI	125 Min
Compression @ 400 psi / 80 min recovery	ASTM F36	%	.0-50
Hardness: Shore A	ASTM D2240	Durometer	60 +/-10
Flexibility	ASTM F147	Factor	3 Max
Fluid Immersion: 70 Hrs. @ 212° F	ASTM F146	%	Volume
Oil 1			-5 to +15
Oil 3			0 to +35
Temperature Range		° F	-40 to 250

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.